



TECHNICAL DATA

FOR HEAT SET MORTAR



BRAND NAME :

NM24 - 80

RAW MATERIAL BASIS :

ALUMINA - BAUXITE

PHYSICAL PROPERTIES :

Grain size , mm	0 – 0.25
Refractoriness test Does not flow from joints when heated for 5 hours at , °C	1600

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	16.4
Al ₂ O ₃	78.0
TiO ₂	2.0
Fe ₂ O ₃	1.2
CaO	0.6
MgO	0.6
Na ₂ O + K ₂ O + Li ₂ O	1.2

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

310693R5