



TECHNICAL DATA

FOR DENSE CASTABLE



BRAND NAME :

NC21 - 15

RAW MATERIAL BASIS :

CHAMOTTE- SILLIMANITE

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1450
Dry castable required , Kg/m ³	2170
Approximate amount of water required for pouring , Liter /25Kg	2.1 – 2.4
Bulk density , Kg/m ³ after drying at 110°C	2250
Cold crushing strength , Kg/cm ² after drying at 110°C	400 – 600
after heating at 1370°C	500 – 700
Permanent Linear Change , % after heating at 1370°C	-1.0 to +1.0
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	41.4
Al ₂ O ₃	48.7
TiO ₂	1.8
Fe ₂ O ₃	1.8
CaO	5.3
Na ₂ O + K ₂ O + Li ₂ O	1.0

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

240997R4