



TECHNICAL DATA

FOR DENSE CASTABLE – ULCC

\*\*\*\*\*



BRAND NAME :

NC21 - 18ULV

TYPE OF PRODUCT :

HIGH ALUMINA

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1880
Dry castable required , Kg/m <sup>3</sup>	3050
Approximate amount of water required for pouring , Liter /30Kg	1.1 – 1.5
Bulk density , Kg/m <sup>3</sup> after drying at 110°C	3100
Cold crushing strength , Kg/cm <sup>2</sup> after drying at 110°C	350 – 500
after heating at 1600°C	1200 – 1500

CHEMICAL ANALYSIS :

(calcined basis)

SiO <sub>2</sub>	0.1
Al <sub>2</sub> O <sub>3</sub>	98.6
Fe <sub>2</sub> O <sub>3</sub>	0.1
CaO	0.8
Na <sub>2</sub> O + K <sub>2</sub> O + Li <sub>2</sub> O	0.4

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

150588F