



TECHNICAL DATA

FOR DENSE GUNNING MIX



BRAND NAME :	NG21 - 17
RAW MATERIAL BASIS :	BAUXITE
PHYSICAL PROPERTIES :	
Maximum service temperature , °C	1500
Dry gunning mix required , Kg/m ³	2300
Approximate amount of water required for pouring , Liter /25Kg	2.4 – 3.0
Bulk density , Kg/m ³ after drying at 110°C	2400
Cold crushing strength , Kg/cm ² after drying at 110°C	200 – 350
after heating at 1430°C	350 – 550
Permanent Linear Change , % after heating at 1430°C	-1.5 to +1.5
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	24.3
Al ₂ O ₃	67.0
TiO ₂	2.6
Fe ₂ O ₃	1.8
CaO	3.2
Na ₂ O + K ₂ O + Li ₂ O	1.1

PACKING IN SACKS OF , Kg **25**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

220499R5