



TECHNICAL DATA
FOR DRY RAMMING MIX



BRAND NAME : **NR24 - 85**
RAW MATERIAL BASIS : **TABULAR ALUMINA - SPINEL - MAGNESITE**
PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1800
Bulk density , Kg/m ³ after ramming and drying at 110°C	3000
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	0.2
Al ₂ O ₃	83.5
Fe ₂ O ₃	0.2
CaO	0.3
MgO	15.5
Na ₂ O + K ₂ O + Li ₂ O	0.3

PACKING IN SACKS OF , Kg **30**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

090495F