



TECHNICAL DATA
FOR WET RAMMING MIX



BRAND NAME :	NR35 - 80
RAW MATERIAL BASIS :	MAGNESITE CHROME
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1600
Approximate amount of water required for Ramming , Liter /30Kg	1.1
Bulk density , Kg/m ³ after ramming and drying at 110°C	2460
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	3.5
Al ₂ O ₃	6.8
Fe ₂ O ₃	7.8
CaO	2.4
MgO	72.0
Cr ₂ O ₃	7.5

PACKING IN SACKS OF , Kg **30/1000**

The data are subject to reasonable variations and therefore should not be used for specification purposes .
ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

230793R4