NASOOZIN ENGINEERING
& PRODUCTION COMPANY
"Refractories"

شرکت تولیدی و مهندسی نسوزین
"سهامی خاص"

TECHNICAL DATA

FOR REFRACTORY GRAIN SIZED MATERIAL

****

BRAND NAME : **NS16 - 30**

RAW MATERIAL BASIS : **SOFTCLAY**

PHYSICAL PROPERTIES :

Grain size , mm **As powder**

CHEMICAL ANALYSIS :

(calcined basis)

SiO_2	60.0
Al_2O_3	29.8
TiO_2	3.0
Fe_2O_3	2.5
CaO	0.6
MgO	0.9
$Na_2O + K_2O + Li_2O$	3.2

PACKING IN SACKS OF , Kg **20**

The data are subject to reasonable variations and therefore should not be used for specification purposes .
ASTM Test Methods , where applicable , used for determination of data .

ES0100F02 120793R3

کارخانه : اصفهان ، کیلومتر ۲۸ جاده مبارکه
شهرک صنعتی سه راهی مبارکه
پست الکترونیک : info@nasoozin.com

دفتر مرکزی : اصفهان ، خیابان بزرگمهر ، نبش بن بست ۱۲ ، ساختمان پارتیکان
طبقه ۲ ، شماره ۲۱ کد پستی : ۸۱۵۳۸ - ۵۵۸۳۱
تلفن : ۳ - ۳۲۶۶۴۲۱۱ - ۰۳۱ فاکس : ۳۲۶۶۴۲۱۰ - ۰۳۱