



TECHNICAL DATA

FOR DENSE CASTABLE



BRAND NAME :	<u>NC21 - 16</u>
RAW MATERIAL BASIS :	CHAMOTTE
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1540
Dry castable required , Kg/m ³	2170
Approximate amount of water required for pouring , Liter /25Kg	2.2 – 2.7
Bulk density , Kg/m ³ after drying at 110°C	2280
Cold crushing strength , Kg/cm ² after drying at 110°C	400 – 550
after heating at 1430°C	500 – 600
Permanent Linear Change , % after heating at 1430°C	-1.0 to +1.0
Grain Size , mm	0 – 8

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	41.2
Al ₂ O ₃	50.0
TiO ₂	2.0
Fe ₂ O ₃	1.7
CaO	4.1
Na ₂ O + K ₂ O + Li ₂ O	1.0

PACKING IN SACKS OF , Kg 25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

300994R16