



TECHNICAL DATA
FOR DENSE CASTABLE – LCC



BRAND NAME :	<u>NC21 - 18LV</u>
TYPE OF PRODUCT :	HIGH ALUMINA
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1880
Dry castable required , Kg/m ³	3050
Approximate amount of water required for pouring , Liter /30Kg	1.05 – 1.35
Bulk density , Kg/m ³ after drying at 110°C	3100
Cold crushing strength , Kg/cm ² after drying at 110°C	700 – 900
after heating at 1600°C	1100 – 1300

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	0.1
Al ₂ O ₃	97.7
Fe ₂ O ₃	0.1
CaO	1.7
Na ₂ O + K ₂ O + Li ₂ O	0.4

PACKING IN SACKS OF , Kg 30

The data are subject to reasonable variations and therefore should not be used for specification purposes .
ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

101088R7