



TECHNICAL DATA

FOR DENSE CASTABLE – LCC



BRAND NAME :

NC21 - 18SPLV

TYPE OF PRODUCT :

ALUMINA SPINEL

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1880
Dry castable required , Kg/m ³	3050
Approximate amount of water required for pouring , Liter /30Kg	1.15 – 1.30
Bulk density , Kg/m ³ after drying at 110°C	3100
Cold crushing strength , Kg/cm ² after drying at 110°C	600 – 800
after heating at 1600°C	1100 – 1300

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	0.1
Al ₂ O ₃	95.4
Fe ₂ O ₃	0.1
CaO	1.8
MgO	2.2
Na ₂ O + K ₂ O + Li ₂ O	0.4

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

200187R1