



TECHNICAL DATA
FOR DRY RAMMING MIX



BRAND NAME :	NR34 - 90
RAW MATERIAL BASIS :	MAGNESITE
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1700
Bulk density , Kg/m ³ after ramming and drying at 110°C	2700
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :
(Calcined basis)

SiO ₂	2.0
Al ₂ O ₃	4.0
Fe ₂ O ₃	4.5
CaO	1.5
MgO	88.0

PACKING IN SACKS OF , Kg **30/1000**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

230793R5