



TECHNICAL DATA

FOR DENSE GUNNING MIX



BRAND NAME :

NG21 - 17

RAW MATERIAL BASIS :

BAUXITE – ANDALUSITE

PHYSICAL PROPERTIES :

Maximum service temperature , °C	1500
Dry gunning mix required , Kg/m ³	2300
Approximate amount of water required for pouring , Liter /25Kg	2.2 – 2.6
Bulk density , Kg/m ³ after drying at 110°C	2410
Cold crushing strength , Kg/cm ² after drying at 110°C	350 – 500
after heating at 1430°C	400 – 600
Permanent Linear Change , % after heating at 1430°C	-1.5 to +1.5
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	29.1
Al ₂ O ₃	63.0
TiO ₂	2.2
Fe ₂ O ₃	1.8
CaO	3.0
Na ₂ O + K ₂ O + Li ₂ O	0.9

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

030601R6