



TECHNICAL DATA

FOR DENSE GUNNING MIX - LCG

\*\*\*\*\*



BRAND NAME :

NG21 – 17EXL

RAW MATERIAL BASIS :

TABULAR ALUMINA - BAUXITE

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1600
Dry gunning mix required , Kg/m <sup>3</sup>	2630
Approximate amount of water required for pouring , Liter /25Kg	1.9 – 2.3
Bulk density , Kg/m <sup>3</sup> after drying at 110°C	2710
Cold crushing strength , Kg/cm <sup>2</sup> after drying at 110°C	400 – 600
after heating at 1430°C	500 – 700
Permanent Linear Change , % after heating at 1430°C	-1.5 to +1.5
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiO <sub>2</sub>	9.8
Al <sub>2</sub> O <sub>3</sub>	84.5
TiO <sub>2</sub>	1.1
Fe <sub>2</sub> O <sub>3</sub>	0.8
CaO	3.0
Na <sub>2</sub> O + K <sub>2</sub> O + Li <sub>2</sub> O	0.8

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

310201F