



TECHNICAL DATA

FOR DENSE CASTABLE – LCC



BRAND NAME :

NC21 – 16ANLV

RAW MATERIAL BASIS :

ANDALUSITE - BAUXITE - CHAMOTTE

PHYSICAL PROPERTIES :

| | |
|---|-------------|
| Maximum service temperature ,°C | 1550 |
| Dry castable required , Kg/m ³ | 2550 |
| Approximate amount of water required for pouring , Liter /25Kg | 1.3 – 1.6 |
| Bulk density , Kg/m ³ after drying at 110°C | 2630 |
| Cold crushing strength , Kg/cm ² after drying at 110°C | 700 – 900 |
| after heating at 1430°C | 700 – 900 |
| Permanent Linear Change , % after heating at 1430°C | 0.0 to +1.5 |
| Grain size, mm | 0 – 5 |

CHEMICAL ANALYSIS :

(calcined basis)

| | |
|--|------|
| SiO ₂ | 33.5 |
| Al ₂ O ₃ | 60.0 |
| TiO ₂ | 1.6 |
| Fe ₂ O ₃ | 1.6 |
| CaO | 2.4 |
| Na ₂ O + K ₂ O + Li ₂ O | 0.9 |

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

140901F