



TECHNICAL DATA

FOR DENSE CASTABLE – LCC

\*\*\*\*\*



BRAND NAME :

NC21 – 16EXLV

RAW MATERIAL BASIS :

CHAMOTTE - BAUXITE

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1600
Dry castable required , Kg/m <sup>3</sup>	2500
Approximate amount of water required for pouring , Liter /25Kg	1.2 – 1.5
Bulk density , Kg/m <sup>3</sup> after drying at 110°C	2550
Cold crushing strength , Kg/cm <sup>2</sup> after drying at 110°C	800 – 1000
after heating at 1350°C	900 – 1400
Permanent Linear Change , % after heating at 1350°C	-1.5 to +1.5
Grain size, mm	0 – 8

CHEMICAL ANALYSIS :

(calcined basis)

SiO <sub>2</sub>	26.9
Al <sub>2</sub> O <sub>3</sub>	65.0
TiO <sub>2</sub>	2.6
Fe <sub>2</sub> O <sub>3</sub>	2.0
CaO	2.5
Na <sub>2</sub> O + K <sub>2</sub> O + Li <sub>2</sub> O	1.0

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

051100F