



TECHNICAL DATA

FOR DENSE CASTABLE – LCC



BRAND NAME :

NC21 - 16LV

RAW MATERIAL BASIS :

CHAMOTTE - BAUXITE

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1570
Dry castable required , Kg/m ³	2450
Approximate amount of water required for pouring , Liter /25Kg	1.3 – 1.6
Bulk density , Kg/m ³ after drying at 110°C	2530
Cold crushing strength , Kg/cm ² after drying at 110°C	700 – 900
after heating at 1430°C	900 – 1400
Permanent Linear Change , % after heating at 1430°C	-1.0 to +1.0
Grain size, mm	0 – 8

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	35.3
Al ₂ O ₃	56.0
TiO ₂	2.4
Fe ₂ O ₃	2.4
CaO	2.5
Na ₂ O + K ₂ O + Li ₂ O	1.4

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

250596R7