



TECHNICAL DATA
FOR DENSE CASTABLE – LCC



BRAND NAME :	NC21 - 17LVMO
RAW MATERIAL BASIS :	BAUXITE
PHYSICAL PROPERTIES :	
Maximum service temperature , °C	1650
Dry castable required , Kg/m ³	2800
Approximate amount of water required for pouring , Liter /30Kg	1.5 – 1.9
Bulk density , Kg/m ³ after drying at 110°C	2970
Cold crushing strength , Kg/cm ² after drying at 110°C	700 – 900
after heating at 1430°C	900 – 1400
Permanent Linear Change , % after heating at 1430°C	-1.5 to +1.5
Grain size, mm	0 – 8

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	11.9
Al ₂ O ₃	80.0
TiO ₂	3.0
Fe ₂ O ₃	1.9
CaO	2.3
Na ₂ O + K ₂ O + Li ₂ O	0.9

PACKING IN SACKS OF , Kg **30**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

160401F