



TECHNICAL DATA
FOR DENSE CASTABLE



BRAND NAME :

NC21 – 17MO

RAW MATERIAL BASIS :

BAUXITE - ANDALUSITE

PHYSICAL PROPERTIES :

Maximum service temperature , °C	1620
Dry castable required , Kg/m ³	2600
Approximate amount of water required for pouring , Liter /30Kg	2.4 – 2.8
Bulk density , Kg/m ³ after drying at 110°C	2710
Cold crushing strength , Kg/cm ² after drying at 110°C	400 – 600
after heating at 1360°C	500 – 700
Permanent Linear Change , % after heating at 1360°C	-1.5 to +1.5
Grain size, mm	0 – 8

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	11.2
Al ₂ O ₃	80.0
TiO ₂	2.6
Fe ₂ O ₃	1.6
CaO	3.7
Na ₂ O + K ₂ O + Li ₂ O	0.9

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

170801F