



TECHNICAL DATA
FOR DENSE CASTABLE – ULCC



BRAND NAME :	<u>NC21 - 17ULV</u>
RAW MATERIAL BASIS :	BAUXITE
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1600
Dry castable required , Kg/m ³	2700
Approximate amount of water required for pouring , Liter /30Kg	1.45 – 1.65
Bulk density , Kg/m ³ after drying at 110°C	2750
Cold crushing strength , Kg/cm ² after drying at 110°C	250 – 350
after heating at 1430°C	900 – 1400
Permanent Linear Change , % after heating at 1430°C	-1.0 to +1.0
Grain size, mm	0 – 8

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	14.7
Al ₂ O ₃	77.5
TiO ₂	3.1
Fe ₂ O ₃	2.5
CaO	1.1
Na ₂ O + K ₂ O + Li ₂ O	1.1

PACKING IN SACKS OF , Kg 30

The data are subject to reasonable variations and therefore should not be used for specification purposes .
ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

060892R1