



TECHNICAL DATA

FOR DENSE CASTABLE



BRAND NAME :

NC21 - 18

RAW MATERIAL BASIS :

TABULAR ALUMINA

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1800
Dry castable required , Kg/m ³	2850
Approximate amount of water required for pouring , Liter /30Kg	2.3 – 2.6
Bulk density , Kg/m ³ after drying at 110°C	2950
Cold crushing strength , Kg/cm ² after drying at 110°C	500 – 700
after heating at 1600°C	600 – 800
Permanent Linear Change , % after heating at 1600°C	-1.0 to +1.0
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	0.2
Al ₂ O ₃	94.5
TiO ₂	0.1
Fe ₂ O ₃	0.1
CaO	3.8
Na ₂ O + K ₂ O + Li ₂ O	0.5

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

150102R15