



TECHNICAL DATA
FOR DENSE COATING MIX



BRAND NAME :	NC21 - 18F
RAW MATERIAL BASIS :	TABULAR ALUMINA
PHYSICAL PROPERTIES :	
Maximum service temperature , °C	1750
Dry material required , Kg/m ³	2200
Approximate amount of water required for coating , Liter /25Kg	3.6 – 4.1
Bulk density , Kg/m ³ after drying at 110°C	2300
Cold crushing strength , Kg/cm ² after drying at 110°C	300 – 400
Grain size, mm	0 – 2

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	10.4
Al ₂ O ₃	81.0
TiO ₂	0.6
Fe ₂ O ₃	0.8
CaO	6.1
Na ₂ O+K ₂ O+Li ₂ O	1.1

PACKING IN SACKS OF , Kg **25**

The data are subject to reasonable variations and therefore should not be used for specification purposes .
ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

(Preliminary Name: NE1 – 88)

171001R7