



TECHNICAL DATA
FOR DENSE CASTABLE



BRAND NAME :	NC31 - 14
RAW MATERIAL BASIS :	CHROMITE
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1370
Dry castable required , Kg/m ³	2570
Approximate amount of water required for pouring , Liter /30Kg	3.3 – 3.7
Bulk density , Kg/m ³ after drying at 110°C	2700
Cold crushing strength , Kg/cm ² after drying at 110°C	250 – 350
after heating at 1320°C	200 – 300
Permanent Linear Change , % after heating at 1320°C	-1.5 to 0.0
Grain size, mm	0 – 4

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	7.0
Al ₂ O ₃	24.4
Fe ₂ O ₃	15.6
CaO	12.6
MgO	14.9
Cr ₂ O ₃	25.5

PACKING IN SACKS OF , Kg **30**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

200398R5