



TECHNICAL DATA

FOR DENSE CASTABLE



BRAND NAME :	NC31 - 15
RAW MATERIAL BASIS :	CHROMITE
PHYSICAL PROPERTIES :	
Maximum service temperature , °C	1550
Dry castable required , Kg/m ³	2800
Approximate amount of water required for pouring , Liter /30Kg	2.0 – 2.5
Bulk density , Kg/m ³ after drying at 110°C	2950
Cold crushing strength , Kg/cm ² after drying at 110°C	450 – 600
after heating at 1430°C	300 – 450
Permanent Linear Change , % after heating at 1430°C	-1.5 to +1.5
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	5.5
Al ₂ O ₃	33.0
Fe ₂ O ₃	12.2
CaO	4.9
MgO	16.2
Cr ₂ O ₃	28.2

PACKING IN SACKS OF , Kg **30**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

200398R12