





## 



BRAND NAME:		NC32 - 16F
RAW MATERIAL BASIS:		MAGNESITE
PHYSICAL PROPERTIES:		
Maximum service temperature, °C		1600
Dry castable required , Kg/m³		1730
Approximate amount of water required for coating, Liter/30Kg		6.9 - 8.4
Bulk density , Kg/m³ after drying at 110°c		1800
Cold crushing strength, Kg/cm <sup>2</sup> after drying at 110°c after heating at 1500°c		15 <b>–</b> 25 10 <b>–</b> 15
Permanent Linear Change, % after heating at 1500°c		-1.5 to +1.5
Grain size, mm		0 – 1
CHEMICAL ANALYSIS: (calcind basis)		
SiO <sub>2</sub>	<b>,</b>	2.9
Al <sub>2</sub> C	=	3.5
Fe <sub>2</sub> C	<b>D</b> <sub>3</sub>	2.6

## PACKING IN SACKS OF, Kg

MgO

CaO

 $Na_2O + K_2O + Li_2O$ 

30

87.5

1.5

2.0

The data are subject to reasonable variations and therefore should not be used for specification purposes.

ASTM Test Methods, where applicable, used for determination of data.

ES0100F02

(Preliminary Name: NE1 – 90)

070994R5

کد پستی : ۵۵۸۳۱ – ۸۱۵۳۸ فاکس : ۳۲۶۶۴۲۱۰ – ۳۱۰ طبقه ۲، شماره ۲۱ تلفن : ۳ – ۳۲۶۶۴۲۱۱ – ۳۱۰