



TECHNICAL DATA

FOR LIGHT WEIGHT GUNNING MIX



BRAND NAME :	NG22 - 16
TYPE OF PRODUCT :	HIGH ALUMINA
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1450
Dry gunning mix required , Kg/m ³	1550
Approximate amount of water required for pouring , Liter /30Kg	4.5 – 5.4
Bulk density , Kg/m ³ after drying at 110°C	1650
Cold crushing strength , Kg/cm ² after drying at 110°C	80 – 120
after heating at 1430°C	100 – 140
Thermal conductivity , Kcal/h.m.°C at 400°C	0.59
600°C	0.61
800°C	0.63

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	38.3
Al ₂ O ₃	51.0
TiO ₂	2.0
Fe ₂ O ₃	1.6
CaO	5.6
Na ₂ O + K ₂ O + Li ₂ O	1.5

PACKING IN SACKS OF , Kg 30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

121189F