



TECHNICAL DATA

FOR DENSE GUNNING MIX - LCG

\*\*\*\*\*



BRAND NAME : NG51 - 15L  
RAW MATERIAL BASIS : CHAMOTTE – BAUXITE – SILICON CARBIDE  
PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1500
Dry gunning mix required , Kg/m <sup>3</sup>	2160
Approximate amount of water required for pouring , Liter /25Kg	2.5 – 2.8
Bulk density , Kg/m <sup>3</sup> after drying at 110°C	2220
Cold crushing strength , Kg/cm <sup>2</sup> after drying at 110°C	100 – 200
after heating at 1430°C	300 – 500
Permanent Linear Change , % after heating at 1430°C	-1.5 to +1.5
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiC	14.9
SiO <sub>2</sub>	33.6
Al <sub>2</sub> O <sub>3</sub>	44.0
TiO <sub>2</sub>	2.0
Fe <sub>2</sub> O <sub>3</sub>	1.9
CaO	2.6
Na <sub>2</sub> O + K <sub>2</sub> O + Li <sub>2</sub> O	1.0

PACKING IN SACKS OF , Kg 25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

301197R1