



## TECHNICAL DATA

### FOR DENSE GUNNING MIX - LCG

\*\*\*\*\*



BRAND NAME :

NG51 - 16L

RAW MATERIAL BASIS :

BAUXITE – SILICON CARBIDE

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1550
Dry gunning mix required , Kg/m <sup>3</sup>	2400
Approximate amount of water required for pouring , Liter /25Kg	2.2 – 2.5
Bulk density , Kg/m <sup>3</sup> after drying at 110°C	2450
Cold crushing strength , Kg/cm <sup>2</sup> after drying at 110°C	150 – 250
after heating at 1430°C	400 – 600
Permanent Linear Change , % after heating at 1430°C	-1.5 to +1.5
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiC	14.9
SiO <sub>2</sub>	17.1
Al <sub>2</sub> O <sub>3</sub>	60.0
TiO <sub>2</sub>	2.5
Fe <sub>2</sub> O <sub>3</sub>	1.8
CaO	2.8
Na <sub>2</sub> O + K <sub>2</sub> O + Li <sub>2</sub> O	0.9

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

301197F