



TECHNICAL DATA

FOR HEAT SET MORTAR



BRAND NAME :

NM24 - 65

RAW MATERIAL BASIS :

ALUMINA - CHAMOTTE

PHYSICAL PROPERTIES :

Grain size , mm

0 – 0.25

Refractoriness test

Does not flow from joints

when heated for 5 hours at , °C

1500

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	27.9
Al ₂ O ₃	65.0
TiO ₂	2.0
Fe ₂ O ₃	1.9
CaO	0.6
MgO	0.6
Na ₂ O + K ₂ O + Li ₂ O	2.0

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

090202R10