



TECHNICAL DATA

FOR HYDRAULIC BOND MORTAR



BRAND NAME :	NM25 - 90
RAW MATERIAL BASIS :	ALUMINA
PHYSICAL PROPERTIES :	
Grain size , mm	0 - 0.25
Refractoriness test	
Does not flow from joints	
when heated for 5 hours at ,°C	1650

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	0.2
Al ₂ O ₃	91.5
Fe ₂ O ₃	0.1
CaO	8.0
Na ₂ O + K ₂ O + Li ₂ O	0.2

PACKING IN SACKS OF , Kg **30**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

(Preliminary Name: NE4 – 83)

090793R5