



TECHNICAL DATA  
FOR DRY RAMMING MIX  
\*\*\*\*\*



BRAND NAME :

NR34 - 80

RAW MATERIAL BASIS :

MAGNESITE CHROME

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1600
Bulk density , Kg/m <sup>3</sup> after ramming and drying at 110°C	2670
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :

(calcined basis)

SiO <sub>2</sub>	3.5
Al <sub>2</sub> O <sub>3</sub>	6.8
Fe <sub>2</sub> O <sub>3</sub>	7.8
CaO	2.4
MgO	72.0
Cr <sub>2</sub> O <sub>3</sub>	7.5

PACKING IN SACKS OF , Kg

30/1000

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

100494R6