



TECHNICAL DATA  
FOR DRY RAMMING MIX  
\*\*\*\*\*



BRAND NAME :

**NR34 - 88**

TYPE OF PRODUCT :

**MAGNESITE SPINEL**

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1600
Bulk density , Kg/m <sup>3</sup> after ramming and drying at 110°C	2700
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiO <sub>2</sub>	0.9
Al <sub>2</sub> O <sub>3</sub>	8.2
Fe <sub>2</sub> O <sub>3</sub>	0.9
CaO	1.5
MgO	88.4
Na <sub>2</sub> O + K <sub>2</sub> O + Li <sub>2</sub> O	0.1

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

250292R1