



TECHNICAL DATA  
FOR DRY RAMMING MIX  
\*\*\*\*\*



BRAND NAME :	<b>NR34 - 95</b>
RAW MATERIAL BASIS :	<b>MAGNESITE</b>
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	<b>1750</b>
Bulk density , Kg/m <sup>3</sup> after ramming and drying at 110°C	<b>2700</b>
Grain size, mm	<b>0 – 6</b>

CHEMICAL ANALYSIS :  
(calcined basis)

SiO <sub>2</sub>	<b>2.3</b>
Al <sub>2</sub> O <sub>3</sub>	<b>0.3</b>
Fe <sub>2</sub> O <sub>3</sub>	<b>0.6</b>
CaO	<b>2.8</b>
MgO	<b>94.0</b>

PACKING IN SACKS OF , Kg **30/1000**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

230793R4