



TECHNICAL DATA

FOR DENSE CASTABLE



BRAND NAME :

NC11 - 13

RAW MATERIAL BASIS :

CHAMOTTE

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1300
Dry castable required , Kg/m ³	2050
Approximate amount of water required for pouring , Liter /25Kg	2.5 – 3.4
Bulk density , Kg/m ³ after drying at 110°C	2100
Cold crushing strength , Kg/cm ² after drying at 110°C	200 – 350
after heating at 1260°C	300 – 450
Permanent Linear Change , % after heating at 1260°C	-1.5 to +1.5
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	43.4
Al ₂ O ₃	41.0
TiO ₂	3.2
Fe ₂ O ₃	4.7
CaO	6.5
Na ₂ O + K ₂ O + Li ₂ O	1.2

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

150102R19