



TECHNICAL DATA

FOR DENSE CASTABLE



BRAND NAME :

NC21 - 17CH

TYPE OF PRODUCT :

ALUMINA CHROMITE

PHYSICAL PROPERTIES :

Maximum service temperature , °C	1650
Dry castable required , Kg/m ³	2600
Approximate amount of water required for pouring , Liter /30Kg	2.3 – 2.8
Bulk density , Kg/m ³ after drying at 110°C	2700
Cold crushing strength , Kg/cm ² after drying at 110°C	500 – 700
after heating at 1430°C	500 – 700

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	6.3
Al ₂ O ₃	71.6
TiO ₂	2.5
Fe ₂ O ₃	4.0
CaO	5.0
MgO	4.6
Cr ₂ O ₃	5.4
Na ₂ O + K ₂ O + Li ₂ O	0.6

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

(Preliminary Name: NE6 – 82)

130691R5