



TECHNICAL DATA
FOR DENSE CASTABLE



BRAND NAME :

NC21 - 17MO

RAW MATERIAL BASIS :

BAUXITE - ANDALUSITE

PHYSICAL PROPERTIES :

Maximum service temperature , °C	1600
Dry castable required , Kg/m ³	2500
Approximate amount of water required for pouring , Liter /30Kg	3.1 – 3.7
Bulk density , Kg/m ³ after drying at 110°C	2590
Cold crushing strength , Kg/cm ² after drying at 110°C	400 – 600
after heating at 1350°C	450 – 650
Permanent Linear Change , % after heating at 1350°C	-1.5 to 0.0
Grain size, mm	0 – 3

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	11.9
Al ₂ O ₃	78.0
TiO ₂	2.3
Fe ₂ O ₃	1.5
CaO	5.4
Na ₂ O + K ₂ O + Li ₂ O	0.9

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

290203R1