



TECHNICAL DATA

FOR DENSE CASTABLE – LCC



BRAND NAME :

NC21 - 18CRLS

TYPE OF PRODUCT :

ALUMINA CHROM

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1800
Dry castable required , Kg/m ³	3000
Approximate amount of water required for pouring , Liter /30Kg	1.44 – 1.74
Bulk density , Kg/m ³ after drying at 110°C	3050
Cold crushing strength , Kg/cm ² after drying at 110°C after heating at 1500°C	550 – 750 1000 – 1500

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	0.1
Al ₂ O ₃	97.1
Fe ₂ O ₃	0.1
CaO	1.4
Cr ₂ O ₃	1.0
Na ₂ O + K ₂ O + Li ₂ O	0.3

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

141187F