



TECHNICAL DATA
FOR DENSE CASTABLE – NCC



BRAND NAME :

NC21 - 18NV

RAW MATERIAL BASIS :

TABULAR ALUMINA

PHYSICAL PROPERTIES :

Maximum service temperature , °C	1800
Dry castable required , Kg/m ³	3050
Approximate amount of hardener liquid required for pouring , Liter /30Kg	2.7 – 3.0
Bulk density , Kg/m ³ after drying at 110°C	3050
Cold crushing strength , Kg/cm ² after drying at 110°C	200 – 400
after heating at 1430°C	1100 – 1400
Permanent Linear Change , % after heating at 1430°C	-1.5 to 0.0
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	3.3
Al ₂ O ₃	96.0
Fe ₂ O ₃	0.2
CaO	0.1
Na ₂ O + K ₂ O + Li ₂ O	0.4

PACKING IN SACKS OF , Kg 30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

060803R2