



TECHNICAL DATA
FOR LIGHT WEIGHT GUNNING MIX



BRAND NAME :	NG12 - 10
RAW MATERIAL BASIS :	CHAMOTTE
PHYSICAL PROPERTIES :	
Maximum service temperature , °C	1000
Dry castable required , Kg/m ³	600
Approximate amount of water required for pouring , Liter /15Kg	12.5 – 14.5
Bulk density , Kg/m ³ after drying at 110°C	630
Cold crushing strength , Kg/cm ² after drying at 110°C	10 – 20
after heating at 800°C	10 – 15
Permanent Linear Change , % after heating at 800°C	-1.5 to 0.0
Grain size, mm	0 – 4

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	47.2
Al ₂ O ₃	25.0
TiO ₂	1.6
Fe ₂ O ₃	6.2
CaO	17.5
Na ₂ O + K ₂ O + Li ₂ O	2.5

PACKING IN SACKS OF , Kg **15**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

140102R3