



TECHNICAL DATA

FOR DENSE GUNNING MIX - LCG



BRAND NAME :

NG51 - 15L

RAW MATERIAL BASIS :

CHAMOTTE – BAUXITE – SILICON CARBIDE

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1500
Dry gunning mix required , Kg/m ³	2160
Approximate amount of water required for pouring , Liter /25Kg	2.5 – 2.8
Bulk density , Kg/m ³ after drying at 110°C	2220
Cold crushing strength , Kg/cm ² after drying at 110°C	100 – 200
after heating at 1430°C	300 – 500
Permanent Linear Change , % after heating at 1430°C	-1.5 to +1.5
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiC	14.9
SiO ₂	33.6
Al ₂ O ₃	44.0
TiO ₂	2.0
Fe ₂ O ₃	1.9
CaO	2.6
Na ₂ O + K ₂ O + Li ₂ O	1.0

PACKING IN SACKS OF , Kg

25

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

301197R1