



TECHNICAL DATA
FOR AIR SET MORTAR



BRAND NAME :	NM15 - 40
TYPE OF PRODUCT :	FIRECLAY
PHYSICAL PROPERTIES :	
Grain size , mm	0 – 0.25
Refractoriness test	
Does not flow from joints when heated for 5 hours at , °C	1400

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	50.4
Al ₂ O ₃	41.0
TiO ₂	2.0
Fe ₂ O ₃	2.7
CaO	1.0
MgO	0.7
Na ₂ O + K ₂ O + Li ₂ O	2.2

PACKING IN SACKS OF , Kg **30**

The data are subject to reasonable variations and therefore should not be used for specification purposes .
ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

280989F