



TECHNICAL DATA

FOR AIR SET MORTAR



BRAND NAME :

NM25 - 85CR

RAW MATERIAL BASIS :

TABULAR ALUMINA - BAUXITE - CHROME

PHYSICAL PROPERTIES :

Grain size , mm	0 – 0.5
Refractoriness test	
Does not flow from joints	
when heated for 5 hours at , °C	1600

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	5.9
Al ₂ O ₃	86.0
Cr ₂ O ₃	5.0
TiO ₂	1.6
Fe ₂ O ₃	0.8
CaO	0.2
Na ₂ O + K ₂ O + Li ₂ O	0.5

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

171001F