



TECHNICAL DATA  
FOR HYDRAULIC BOND MORTAR  
\*\*\*\*\*

BRAND NAME :	<b>NM25 - 90</b>
RAW MATERIAL BASIS :	<b>ALUMINA</b>
PHYSICAL PROPERTIES :	
Grain size , mm	<b>0 – 0.25</b>
Refractoriness test	
Does not flow from joints when heated for 5 hours at ,°C	<b>1650</b>

CHEMICAL ANALYSIS :  
(calcined basis)

SiO <sub>2</sub>	<b>0.2</b>
Al <sub>2</sub> O <sub>3</sub>	<b>91.5</b>
Fe <sub>2</sub> O <sub>3</sub>	<b>0.1</b>
CaO	<b>8.0</b>
Na <sub>2</sub> O + K <sub>2</sub> O + Li <sub>2</sub> O	<b>0.2</b>

PACKING IN SACKS OF , Kg **30**

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

(Preliminary Name: NE4 – 83)

090793R5