



TECHNICAL DATA

FOR AIR SET MORTAR



BRAND NAME :

NM35 - 80

RAW MATERIAL BASIS :

MAGNESITE

PHYSICAL PROPERTIES :

Grain size , mm

0 – 0.25

Refractoriness test

Does not flow from joints

when heated for 5 hours at , °C

1650

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	10.7
Al ₂ O ₃	3.2
Fe ₂ O ₃	5.0
CaO	1.7
MgO	74.6
Cr ₂ O ₃	4.0
Na ₂ O + K ₂ O + Li ₂ O	0.8

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

090793R4