



**TECHNICAL DATA
FOR AIR SET PLASTIC



BRAND NAME :	NP25 - 75
RAW MATERIAL BASIS :	BAUXITE
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1650
Amount required for ramming , Kg/m ³	2750
Bulk density , Kg/m ³ after drying at 110°C	2550
Cold crushing strength , Kg/cm ² after drying at 110°C	80 – 100
after heating at 1600°C	180 – 250

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	10.7
Al ₂ O ₃	76.3
TiO ₂	3.5
Fe ₂ O ₃	2.8
CaO	0.6
Na ₂ O + K ₂ O + Li ₂ O	1.0
P ₂ O ₅	5.1

PACKING IN CARTONS OF , Kg **25**

The data are subject to reasonable variations and therefore should not be used for specification purposes .
ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

280995R5