



TECHNICAL DATA
FOR DRY RAMMING MIX



BRAND NAME :

NR34 - 85

RAW MATERIAL BASIS :

MAGNESITE - ALUMINA

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1600
Bulk density , Kg/m ³ after ramming and drying at 110°C	2750
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	3.2
Al ₂ O ₃	10.1
Fe ₂ O ₃	0.5
CaO	2.2
MgO	84.0

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

230793R7