



TECHNICAL DATA
FOR DRY RAMMING MIX



BRAND NAME :

NR34 - 88

TYPE OF PRODUCT :

MAGNESITE SPINEL

PHYSICAL PROPERTIES :

Maximum service temperature ,°C	1600
Bulk density , Kg/m ³ after ramming and drying at 110°C	2700
Grain size, mm	0 – 5

CHEMICAL ANALYSIS :

(calcined basis)

SiO ₂	0.9
Al ₂ O ₃	8.2
Fe ₂ O ₃	0.9
CaO	1.5
MgO	88.4
Na ₂ O + K ₂ O + Li ₂ O	0.1

PACKING IN SACKS OF , Kg

30

The data are subject to reasonable variations and therefore should not be used for specification purposes .

ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

250292R1