



TECHNICAL DATA
FOR DRY RAMMING MIX



BRAND NAME :	NR34 - 95
RAW MATERIAL BASIS :	MAGNESITE
PHYSICAL PROPERTIES :	
Maximum service temperature ,°C	1750
Bulk density , Kg/m ³ after ramming and drying at 110°C	2700
Grain size, mm	0 – 6

CHEMICAL ANALYSIS :
(calcined basis)

SiO ₂	2.3
Al ₂ O ₃	0.3
Fe ₂ O ₃	0.6
CaO	2.8
MgO	94.0

PACKING IN SACKS OF , Kg **30/1000**

The data are subject to reasonable variations and therefore should not be used for specification purposes .
ASTM Test Methods , where applicable , used for determination of data .

ES0100F02

230793R4